

ROKU® AC Sealant

Material of building material classification B2 (normal flammability) according to DIN 4102-1

General building approval Z-19.11-1941

Product Description

The putty-like, pasty and foaming construction material expands without foaming pressure from a temperature of ca. 200 °C; its direction of action is mainly 2 dimensional.



Application Areas

- Fire protection windows and doors
- Expansion joints
- Pipe and cable ducts

Technical Data

| | |
|-----------------------------------|---|
| Composition: | Halogen free, foaming construction material based on Acrylate |
| Material structure: | Putty-like |
| Raw density [kg/m ³]: | 1360 to 1840 |
| Start of reaction [°C]: | From ca. 200 |
| Foaming rate [x-times]: | 1,9 to 5-times (400 °C; 30 min; without load) |
| Direction of action: | Flat |
| Forming inflatable body: | Stable mass |

Supplied Forms

310 ml cartridge

Please read the safety data sheet!

Processing and Storage

Processing: Use commercially available cartridge guns or a spatula to apply
Storage: Store in a dry place between +2 °C and +49 °C; original, closed containers can be stored ca. 24 months after date of filling.

*Ensure that surfaces are free from dust, fat or oil! Close opened cartridges air-tight and use as fast as possible!
Protect from frost or heat!*

Note

The information in this brochure is based on our knowledge and experience to date. This information does not release the user from carrying out independent tests and trials due to the various influences when processing and applying our product. It is not possible to derive a guarantee of certain properties or suitability of the product in a concrete application case based on our information. All the descriptions, drawings, photographs, data, conditions, weights etc. included may change without previous announcement; they do not constitute the contractually agreed property of the product. The recipient of our product is responsible to observe any trade mark rights and existing laws and regulations.
Corresponds to DIN 2304.